

POLYARYLENE COPOLYMER AND PROTON-CONDUCTIVE FILM

Patent number: JP2001329053
Publication date: 2001-11-27
Inventor: GOTO KOHEI; YAMAKAWA YOSHITAKA; ROZHANSKI
IGOR
Applicant: JSR CORP
Classification:
- international: C08G61/12; H01B1/12; H01G9/028; H01M8/02;
H01M6/18; H01M10/40
- european:
Application number: JP20000153047 20000524
Priority number(s): JP20000153047 20000524

Report a data error here

Abstract of JP2001329053

PROBLEM TO BE SOLVED: To provide a polyarylene copolymer capable of giving a sulfonated polymer capable of forming a film exhibiting a high proton-conductivity over a wide temperature range, and having excellent mechanical strengths, suppressed swellability in hot water and excellent durability by controlling an amount of a sulfonic acid introduced not to deteriorate the mechanical properties.
SOLUTION: Provided are a polyarylene copolymer comprising 40-3 mol% (A) units of an aromatic compound having electron-attracting groups and etheric bonds in the main chain and 60-97 mol% [(A)+(B)=100 mol%] (B) units of an aromatic compound having no electron-attracting groups in the main chain and a protonically conductive film comprising a sulfonated polymer prepared by sulfonating the copolymer.

Data supplied from the **esp@cenet** database - Worldwide